

FORMPOLY® SANGF30

(30% Glass Fiber Reinforced SAN)

GENERAL

FPL offers a range of Engineering Plastic grades from unfilled to glass fibre reinforced including **FORMPOLY® SANGF30**, which is Glass Fibre reinforced ABS with excellent mechanical and thermal properties.

FORMPOLY® SANGF30

Low warpage
Easy flow and fast solidification
Good dimensional stability
High mechanical properties
Excellent dimensional stability

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 80°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY® SANGF30 is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Textile pulleys
Air conditioner fans
Impellers
Motor casing
Speedometer housing for OTR vehicles

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	95
Elongation at Break	D638	%	3
Flexural Stress	D790	MPa.	130
Flexural Modulus	D790	MPa.	7000
Izod Impact Strength Notched	D256	Kg cm/cm	7
Heat Deflection Temp			
- at 4.6 Kg/cm ² load	D648	°C	115
- at 18.5 Kg/cm ² load			110
Specific Gravity	D792	-	1.27
Shrinkage parallel	D955	%	0.1 to 0.3

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D4203

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:26811275 E Mail: info@formulatedpolymers.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India..

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

