

# FORMPOLY® POMGF30 (30% Glass Reinforced POM)

## GENERAL

FPL offers a range of Polyoxymethylene grades from unfilled, glass fibre reinforced to flame retardant including **FORMPOLY® POMGF30**, which is heat stabilized, glass reinforced POM with excellent mechanical / thermal properties and reduced shrinkage.

### FORMPOLY® POMGF30

Smooth surface finish  
Moderate flow and fast solidification  
High heat resistance.  
Warpage free molding  
Easy processability  
UV Stability  
Excellent dimensional stability

## PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100°C for 2 to 3 hours for good surface finish.

## PACKING

**FORMPOLY® POMGF30** is supplied in 25 Kgs dry, ready to mould, in sealed bags to prevent the uptake of moisture.

## APPLICATION

Spool gears  
Bushes  
Cams  
Rollers

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa	135
Elongation at Break	D638	%	2.5
Flexural Stress	D790	MPa	160
Flexural Modulus	D790	MPa	7800
Izod Impact Strength Notched	D256	kg.cm/cm	8
Heat Deflection Temp - at 18.5 kg/cm <sup>2</sup> load	D648	°C	160
Specific Gravity	D792	-	1.60
Shrinkage	D955	%	1.6-2.0

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen  
Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

## FORMULATED POLYMERS LIMITED

### Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:26811275 E Mail: info@formulatedpolymers.com

URL: [www.formulatedpolymers.com](http://www.formulatedpolymers.com)

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.

**ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm**

