

FORMPOLY® PPOGF20

(20% Glass Fibre Reinforced PPO)

GENERAL

FPL offers a range of Engineering Plastic grades from unfilled, glass fibre reinforced to flame retardant for most demanding conditions and extreme requirements including **FORMPOLY® PPOGF20**, which is Glass Fibre Reinforced PPO with high stiffness.

FORMPOLY® PPOGF20

High heat resistance
Low warpage
Good surface finish
Easy flow and fast solidification
Easy processability

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 80°C for 1 to 2 hours for good surface finish.

PACKING

FORMPOLY® PPOGF20 is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Electrical meter parts
Automotive Ignitions
Motor housing
Ampere meter parts
Flow regulators

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	80
Elongation at Break	D638	%	3
Flexural Stress	D790	MPa.	130
Flexural Modulus	D790	MPa.	5000
Izod Impact Strength Notched	D256	Kg cm/cm	20
Heat Deflection Temp - at 18.5 Kg/cm ² load	D648	°C	130
Specific Gravity	D792	-	1.24
Shrinkage	D955	%	0.2-0.4
Water absorption at Equilibrium	D570	%	0.10
Vicat VST/B/120	D1525	C	140

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.



ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm