

FORMPOLY N66GF35LT

(35%Glass Fibre Reinforced Nylon66)

GENERAL

FPL offers a range of Nylon66 grades from unfilled, glass fibre reinforced, and mineral reinforced to flame retardant including **FORMPOLY N66GF35LT**, which is heat stabilized, lubricated Glass Fibre Reinforced Nylon 66 with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY N66GF35LT

Easy flow and Fast solidification
Lubricated and heat stabilized
High mechanical properties
Excellent dimensional stability
Low Moisture absorption

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY N66GF35LT is supplied in 25 Kg dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Radiator fans
Radiator shroud
Instrument Housings
Switch assembly
Housings

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	180
Elongation at Break	D638	%	4
Flexural Stress	D790	MPa.	250
Flexural Modulus	D790	MPa.	9000
Izod Impact Strength Notched	D256	Kg cm/cm	13
Heat Deflection Temp		°C	
- at 4.6 Kg/cm ² load	D648		220
- at 18.5 Kg/cm ² load			220
Specific Gravity	D792	-	1.39
Shrinkage	D955	%	0.15 – 0.3
Volume Resistivity	D257	Ohms-cm	10 ¹⁵
Surface Resistivity	D257	Ohms	10 ¹⁴

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:26811275 E Mail: formpoly@vsnl.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.



A ISO/TS 16949. ISO 9001 & ISO 14001 & ISO 18000 certified