

# FORMPOLY®N66TPF30

## (Unfilled Nylon 66-Heat Stabilized)

### GENERAL

FPL offers a wide range of Nylon66 grades from unfilled, glass fiber reinforced, mineral reinforced to flame retardant including **FORMPOLY® N66TPF30** which is easy flow and low melt viscosity primarily intended for Injection moulding, with enhanced tribological properties for unlubricated systems.

### FORMPOLY® N66TPF30

Easy flow and Fast solidification.  
Good Chemical resistance  
Available in variable colours  
Easy flow fast solidification  
Fine crystalline structure

### PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100°C for 2 to 3 hours for good surface finish.

### PACKING

**FORMPOLY® N66TPF30** is supplied in 25 Kgs. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

### APPLICATION

Locknut fasteners  
Motor insulation parts  
Terminals/Connectors  
Electrical Knobs  
Fuse Box

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa	80
Elongation at Break	D638	%	30
Flexural Stress	D790	MPa	110
Flexural Modulus	D790	MPa	2800
Izod Impact Strength Notched	D256	kg.cm/cm	6
Heat Deflection Temp			
- at 4.6 kg/cm <sup>2</sup> load	D648	°C	150
- at 18.5 kg/cm <sup>2</sup> load	D648	°C	75
Specific Gravity	D792	-	1.14
Shrinkage	D955	%	1.5-1.8
Volume Resistivity	D257	Ohms-cm	10E15
Surface Resistivity	D257	Ohms	10E14

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

## FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: [www.formulatedpolymers.com](http://www.formulatedpolymers.com)

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

