

# FORMPOLY® SN66GF35LT

## (35% Glass Fibre Reinforced Nylon66)

### GENERAL

FPL offers a range of Nylon66 grades from unfilled, glass fibre reinforced, and mineral reinforced to flame retardant including **FORMPOLY® SN66GF35LT**, which is heat stabilized, lubricated Glass Fibre Reinforced Nylon 66 with excellent mechanical / thermal properties and reduced shrinkage.

### FORMPOLY® SN66GF35LT

Easy flow and Fast solidification  
Lubricated and heat stabilized  
High mechanical properties  
Excellent dimensional stability  
Low Moisture absorption

### PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100°C for 2 to 3 hours for good surface finish.

### PACKING

**FORMPOLY® SN66GF35LT** is supplied in 25 Kg dry, ready to mould, in sealed bags to prevent the uptake of moisture.

### APPLICATION

Radiator fans  
Radiator shroud  
Instrument Housings  
Switch assembly  
Housings

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa	210
Elongation at Break	D638	%	4
Flexural Stress	D790	MPa	270
Flexural Modulus	D790	MPa	9500
Izod Impact Strength Notched	D256	kg.cm/cm	13
Heat Deflection Temp			
- at 4.6 kg/cm <sup>2</sup> load	D648	°C	255
- at 18.5 kg/cm <sup>2</sup> load	D648	°C	250
Specific Gravity	D792	-	1.40

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

## FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: [www.formulatedpolymers.com](http://www.formulatedpolymers.com)

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.

**ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm**

