

FORMPOLY PPOGF10FR

(10%GF Reinforced PPO-FR Grade)

GENERAL

FPL offers a range of Engineering Plastic grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant for most demanding conditions and extreme requirements including FORMPOLY PPOGF10FR, which is Glass Fibre Reinforced PPO with flame retardant.

FORMPOLY PPOGF10FR

Meeting UL-94V0 requirements
Free from Halogens and Bromine
Warpage free
Excellent electrical properties
Low moisture absorption
Excellent dimensional stability

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 80°C for 1 to 2 hours for good surface finish.

PACKING

FORMPOLY PPOGF10FR is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Internal switch housings
Telecommunication connectors
Deflection yokes
Bobbins
TV parts

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	70
Elongation at Break	D638	%	5
Flexural Stress	D790	MPa.	120
Flexural Modulus	D790	MPa.	4000
Izod Impact Strength Notched	D256	Kg cm/cm	9.5
Heat Deflection Temp - at 18.5 Kg/cm ² load	D648	°C	130
Specific Gravity	D792	-	1.16
Shrinkage	D955	%	0.3-0.5
Water absorption at Equilibrium	D570	%	0.22
Vicat VST/B/120	D1525	°C	140

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.



A ISO/TS 16949. ISO 9001 & ISO 14001 & ISO 18000 certified