FORMPOLY SN6KM14 (25% Mineral Reinforced Nylon6- Meets UL-94V2)

GENERAL

FPL offers a range of Nylon 6 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including **SN6KM14**, which is Glass with selected fibre minerals reinforced flame retardant grade meeting UL-94 V2 requirements with high modulus.

FORMPOLY SN6KM14

Flame retardant grade with Excellent stiffness.

Meeting UL-94 V2 rating in 0.8mm thickness

Meeting RoHS compliances fully. High Glow wire flammability index with low dripping

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 90'C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY SN6KM14 is supplied in 25 Kg dry, ready to mould, in sealed bags to prevent the uptake of moisture. **APPLICATION**

Instrument Housing Switch parts Bush holder Connectors PCB frame

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	70
Elongation at Break	D638	%	2.5
Tensile Modulus	D 638	Мра	7200
Izod Impact Strength Notched	D256	Kg Cm/ Cm	4
Heat Deflection Temp unannealed - at 4.6 Kg / Cm2 load - at 18.5 Kg / Cm2 load	D648	'C	215 200
Specific Gravity	D792	-	1.39
Shrinkage ,flow	D955	%	0.4- 0.6
Flammability(0.75mm)	UL-94	-	V2
GWFI @ 1.6 mm	IEC 60695	С	960

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066 The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED Manufacturers of Engineering Plastics Compounds Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com URL: www.formulatedpolymers.com H0 & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 602 107 India.



A ISO/TS 16949, ISO 9001 & ISO 14001 certified Firm