

FORMPOLY® SN6MF25FR2

(25% Mineral Reinforced Nylon 6- Meets UL-94V2)

GENERAL

FPL offers a range of Nylon 6 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including **FORMPOLY® SN6MF25FR2**, which is a selected minerals reinforced flame retardant grade meeting UL-94 V2 requirement.

FORMPOLY® SN6MF25FR2

Flame retardant grade with Excellent stiffness.

Meeting UL-94 V2 rating in 0.8mm thickness

Meeting RoHS compliances fully.

High Glow wire flammability index

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 90°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY® SN6MF25FR2 is supplied in 25 Kg dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Instrument Housing
Switch parts
Bush holder
Connectors
PCB frame

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa	70
Elongation at Break	D638	%	2.5
Tensile Modulus	D 638	Mpa	7200
Izod Impact Strength Notched	D256	kg.cm/ cm	4
Heat Deflection Temp			
- at 4.6 kg / cm ² load	D648	°C	215
- at 18.5 kg / cm ² load	D648	°C	200
Specific Gravity	D792	-	1.39
Flammability(1.6mm)	UL-94	-	V2
GWFI @ 1.6 mm	IEC 60695	C	960

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India..

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm



PROCESS PARAMETERS SUGGESTED

PROCESSING PARAMETERS	FORMPOLY® SN6MF25FR2
Drying Temperature	80°c
Drying Time	4Hrs
Feed Zone Temp	240-250°c
Compression Zone Temp	250-260°c
Metering Zone Temp	250-270°c
Nozzle Temp	260-270°c
Melt Temp	250-270°c
Mould temp	50-90°c

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India..

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

