FORMPOLY® SN6MF30 (30% Mineral Reinforced Nylon6)

GENERAL

FPL offers a range of Nylon6 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including FORMPOLY® SN6MF30, which is lubricated mineral filled Nylon 6 with excellent mechanical / thermal properties and reduced shrinkage

FORMPOLY® SN6MF30

Low warping High heat resistance Moderate mechanical properties Excellent dimensional stability

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to predry the material at 100°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY® SN6MF30 is supplied in 25 Kg dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Automotive parts Wheel covers MCB housing Lamp housing Handle

Property	ASTM	Unit	Value
	Method		
Tensile Stress	D638	MPa	75
Elongation at Break	D638	%	10
Flexural Modulus	D790	MPa	4000
Tensile Modulus	D 638	Mpa	4400
Izod Impact Strength Notched	D256	kg.cm/cm	7
Heat Deflection Temp			
- at 18.5 kg/cm²load	D648	°C	80
Specific Gravity	D792	_	1.37
Flammability(1.6mm)	UL-94	-	НВ

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com URL: www.formulatedpolymers.com



ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

