# **FORMPOLY N66MF15** (15%Mineral Reinforced Nylon66)

#### **GENERAL**

FPL offers a range of Nylon66 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including FORMPOLY N66MF15, which is heat stabilized, lubricated mineral Reinforced Nylon 66 with excellent mechanical / thermal properties and reduced shrinkage.

#### FORMPOLY N66MF15

Low warping High heat resistance Moderate mechanical properties Excellent dimensional stability Easy paintable

#### **PRE-DRYING**

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100'C for 2 to 3 hours for good surface finish.

#### **PACKING**

FORMPOLY N66MF15 is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

#### **APPLICATION**

Automotive parts Wheel covers MCB housing Lamp housing Handle

Property	ASTM	Unit	Value
	Method		
Tensile Stress	D638	MPa.	80
Elongation at Break	D638	%	10
Flexural Stress	D790	MPa.	125
Flexural Modulus	D790	MPa.	4300
Izod Impact Strength Notched	D256	Kg Cm/ Cm	7
Heat Deflection Temp - at 4.6 Kg / Cm2 load - at 18.5 Kg / Cm2 load	D646	,C	175 110
Specific Gravity Shrinkage	D792 D955	- %	1.23 0.7-0.8
Volume Resistivity	D-257	Ohms-cm	10 <sup>14</sup>
Surface Resistivity	D-257	Ohms	10 <sup>13</sup>

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

## FORMULATED POLYMERS LIM

### Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com URL: www.formulatedpolymers.com HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India

