FORMPOLY N66MF30 (30%Mineral Reinforced Nylon66)

GENERAL

FPL offers a range of Nylon66 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including *FORMPOLY* N66MF30, which is heat stabilized, lubricated mineral Reinforced Nylon 66 with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY N66MF30

Low warping
High heat resistance
Moderate mechanical properties
Excellent dimensional stability
Easy paintable

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100'C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY N66MF30 is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Automotive parts Wheel covers MCB housing Lamp housing Handle

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	80
Elongation at Break	D638	%	6
Flexural Stress	D790	MPa.	170
Flexural Modulus	D790	MPa.	7500
Izod Impact Strength Notched	D256	Kg Cm/ Cm	7
Heat Deflection Temp - at 4.6 Kg / Cm2 load - at 18.5 Kg / Cm2 load	D646	'C	200 190
Specific Gravity	D792	-	1.36
Shrinkage	D955	%	0.2-0.3
Volume Resistivity	D-257	Ohms-cm	10 ¹⁴
Surface Resistivity	D-257	Ohms	10 ¹³

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com URL: www.formulatedpolymers.com HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India



A ISO/TS 16949, ISO 9001 & ISO 14001 certified Firm