FORMPOLY® N66GF33LT (33% Glass Fibre Reinforced Nylon66)

GENERAL

FPL offers a range of Nylon66 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including FORMPOLY® N66GF33LT, which is heat stabilized, lubricated Glass Fibre Reinforced Nylon 66 with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY® N66GF33LT

Easy flow and Fast solidification Lubricated and heat stabilized High mechanical properties Excellent dimensional stability Low Moisture absorption

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to predry the material at 100°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY® N66GF33LT is supplied in 25 Kg dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Radiator fans Radiator shroud Instrument Housings Switch assembly Housings

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa	190
Elongation at Break	D638	%	4
Flexural Stress	D790	MPa	270
Flexural Modulus	D790	MPa	9000
Izod Impact Strength Notched	D256	kg.cm/cm	13
Heat Deflection Temp			
- at 4.6 kg/cm² load	D648	°C	250
- at 18.5 kg/cm²load	D648	°C	245
Specific Gravity	D792	-	1.38
Shrinkage	D955	%	0.15-0.3
Volume Resistivity	D-257	Ohms-cm	10 ¹⁵
Surface Resistivity	D-257	Ohms	1014

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India..

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

