FORMPOLY® N66GP30T (Unfilled Nylon 66 -Impact Modified grade)

GENERAL

FPL offers a range of Nylon66 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including FORMPOLY® N66GP30T, which is heat stabilized Glass Fibre Reinforced Nylon 66 with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY® N66GP30T

Easy flow and Fast solidification Heat stabilized and toughened Excellent dimensional stability Low Moisture absorption

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to predry the material at 100°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY® N66GP30T is supplied in 25 Kg dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Locknut fasteners Motor insulation parts Terminals/Connectors Electrical Knobs Fuse Box

Property	ASTM	Unit	Value
	Method		
Tensile Stress	D638	MPa	75
Elongation at Break	D638	%	30
Flexural Stress	D790	MPa	110
Flexural Modulus	D790	MPa	2500
Izod Impact Strength	D256	kg.cm/cm	11
Notched			
Heat Deflection Temp			
- at 4.6 kg/cm² load	D648	°C	140
- at 18.5 kg/cm² load	D648	°C	70
Specific Gravity	D792	_	1.13
Shrinkage	D955	%	1.5-1.8
Volume Resistivity	D-257	Ohms-cm	10 ¹⁵
Surface Resistivity	D-257	Ohms	1O ¹⁴

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

