## FORMPOLY® SN66GF25HSLR

# (25% Glass Fibre Reinforced Nylon66-Glycol Resistant)

#### **GENERAL**

FPL offers a range of Nylon66 grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including FORMPOLY® SN66GF25HSLR, which is heat stabilized, lubricated Glass Fibre Reinforced Nylon 66 with excellent mechanical / thermal properties and reduced shrinkage.

## FORMPOLY® SN66GF25HSLR

High heat and Glycol resistant Excellent chemical resistance Good gloss and surface finish Excellent dimensional stability Easy Processability

#### **PRE-DRYING**

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to predry the material at 100°C for 2 to 3 hours for good surface finish.

## **PACKING**

FORMPOLY® SN66GF25HSLR is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

### **APPLICATION**

High heat automotive applications Radiation fans Radiator shroud Switch assembly Coil former

FORMPOLY SN66GF25HSLR

| Property  | ASTM<br>Method | Unit     | Value      |
|---|----------------|----------|------------|
| Tensile Stress  | D638           | MPa.     | 175        |
| Elongation at Break   | D638           | %        | 4.5        |
| Flexural Stress   | D790           | MPa.     | 245        |
| Flexural Modulus  | D790           | MPa.     | 8000       |
| Izod Impact Strength Notched                                    | D256           | Kg cm/cm | 14         |
| Heat Deflection Temp - at 4.6 Kg/cm² load - at 18.5 Kg/cm² load | D648           | °C       | 250<br>230 |
| Specific Gravity  | D792           | _        | 1.32       |
| Shrinkage   | D955           | %        | 0.15-0.3   |
| Volume Resistivity  | D257           | Ohms-cm  | 10E14      |
| Surface Resistivity   | D257           | Ohms     | 10E15      |

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

## FORMULATED POLYMERS LIMITED

## **Manufacturers of Engineering Plastics Compounds**

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.

ISO 9001:2015. IATF 16949: 2009 & ISO 14001: 2015 Certified **Firm** 

