

**DESCRIPTION** Starflam AFR470X2 is a Red Phosphorous Flame Retardant, Glass Fiber Reinforced Polyamide 66 Injection Molding Resin

PROPERTY (1)	UNIT	STANDARD	TYPICAL VALUE (1) Dry As Moulded
--------------	------	----------	-------------------------------------

### PHYSICAL

Density	g/cm <sup>3</sup>	ISO 1183	1.43
Moisture Absorption (23°C / 50% RH)	%	ISO 62	1.1
Mold Shrinkage on Tensile Bar, flow	%	E2P Method	0.2 - 0.3
Water Absorption, (23°C/sat)	%	ISO 62	4.5

### MECHANICAL

Flexural Modulus, 2 mm/min	MPa	ISO 178	10250
Flexural Stress, break, 2 mm/min	MPa	ISO 178	260
Hardness, Rockwell L		ISO 2039-2	108
Tensile Modulus, 1 mm/min	MPa	ISO 527	11000
Tensile Strain, break, 5 mm/min	%	ISO 527	3
Tensile Stress, break, 5 mm/min	MPa	ISO 527	175

### IMPACT

Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	kJ/m <sup>2</sup>	ISO 179/1eU	70
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	kJ/m <sup>2</sup>	ISO 179/1eA	11
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	kJ/m <sup>2</sup>	ISO 179/1eU	70
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	kJ/m <sup>2</sup>	ISO 179/1eA	9
Izod Impact, notched 80*10*4 +23°C	kJ/m <sup>2</sup>	ISO 180/1A	12
Izod Impact, notched 80*10*4 -20°C	kJ/m <sup>2</sup>	ISO 180/1A	10
Izod Impact, notched 80*10*4 -30°C	kJ/m <sup>2</sup>	ISO 180/1A	9

Source RJF, last update 01-07-2010

(1) Typical values for natural color unless specified otherwise. Do not constitute a specification. Significant variations are possible for colors

Starflam, Staramide and Starpylen are registered trademarks of EUROSTAR Engineering Plastics

All information, recommendation or advice giving by Eurostar Engineering Plastics Company, or any of its subsidiaries, affiliates or authorized representatives, is given in good faith. Eurostar Engineering Plastics makes no warranty or guarantee, express or implied about the information provided. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of Eurostar Engineering Plastics, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. Eurostar Engineering Plastics cannot be held responsible respectively liable for any loss incurred through the use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Eurostar Engineering Plastics or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

EUROSTAR Engineering Plastics, ZI - Rue de la Ferme Saint Ladre, BP2, F/95471 Fosses Cedex FRANCE,

Tel: + 33 1 34 47 47 00, Fax: + 33 1 34 47 47 18 - [www.eurostar-ep.com](http://www.eurostar-ep.com)

**DESCRIPTION** Starflam AFR470X2 is a Red Phosphorous Flame Retardant, Glass Fiber Reinforced Polyamide 66 Injection Molding Resin

PROPERTY (1)	UNIT	STANDARD	TYPICAL VALUE (1) Dry As Moulded
--------------	------	----------	-------------------------------------

### IMPACT

Izod Impact, notched 80*10*4 -40°C	kJ/m <sup>2</sup>	ISO 180/1A	8
------------------------------------	-------------------	------------	---

### THERMAL

Ball Pressure Test, 125°C +/- 2°C		IEC 60695-10-2	PASSES
CTE, 23°C to 60°C, flow	1/°C	ISO 11359-2	2.10E-05
CTE, 23°C to 60°C, xflow	1/°C	ISO 11359-2	1.50E-05
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	°C	ISO 75/Ae	248
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	°C	ISO 75/Be	255
Relative Temp Index, Elec	°C	UL 746B	100
Relative Temp Index, Mech w/impact	°C	UL 746B	95
Relative Temp Index, Mech w/o impact	°C	UL 746B	100
Vicat Softening Temp, Rate B/120	°C	ISO 306	245
Vicat Softening Temp, Rate B/50	°C	ISO 306	245

### FLAME CHARACTERISTICS

Glow Wire Flammability Index 960°C, passes at	mm	IEC 60695-2-12	2
Oxygen Index (LOI)	%	ISO 4589	28
UL Recognized, 94V-0 Flame Class Rating	mm	UL 94	0.75

### ELECTRICAL

Comparative Tracking Index	V	IEC 60112	600
Dielectric Strength, in oil, 3.2 mm	kV/mm	IEC 60243-1	16
Dissipation Factor, 1 MHz		IEC 60250	0.0142

Source RJF, last update 01-07-2010

(1) Typical values for natural color unless specified otherwise. Do not constitute a specification. Significant variations are possible for colors

Starflam, Staramide and Starpylen are registered trademarks of EUROSTAR Engineering Plastics

All information, recommendation or advice giving by Eurostar Engineering Plastics Company, or any of its subsidiaries, affiliates or authorized representatives, is given in good faith. Eurostar Engineering Plastics makes no warranty or guarantee, express or implied about the information provided. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of Eurostar Engineering Plastics, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. Eurostar Engineering Plastics cannot be held responsible respectively liable for any loss incurred through the use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Eurostar Engineering Plastics or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

EUROSTAR Engineering Plastics, ZI - Rue de la Ferme Saint Ladre, BP2, F/95471 Fosses Cedex FRANCE,

Tel: + 33 1 34 47 47 00, Fax: + 33 1 34 47 47 18 - [www.eurostar-ep.com](http://www.eurostar-ep.com)

**DESCRIPTION** Starflam AFR470X2 is a Red Phosphorous Flame Retardant, Glass Fiber Reinforced Polyamide 66 Injection Molding Resin

PROPERTY (1)	UNIT	STANDARD	TYPICAL VALUE (1) Dry As Moulded
--------------	------	----------	-------------------------------------

### ELECTRICAL

Dissipation Factor, 50/60 Hz		IEC 60250	0.0061
Relative Permittivity, 1 MHz		IEC 60250	3.2
Relative Permittivity, 50/60 Hz		IEC 60250	4.5
Surface Resistivity, ROA	Ohm	IEC 60093	>1.E+15
Volume Resistivity	Ohm-cm	IEC 60093	>1.E+15

Source RJF, last update 01-07-2010

(1) Typical values for natural color unless specified otherwise. Do not constitute a specification. Significant variations are possible for colors

Starflam, Staramide and Starpylen are registered trademarks of EUROSTAR Engineering Plastics

All information, recommendation or advice giving by Eurostar Engineering Plastics Company, or any of its subsidiaries, affiliates or authorized representatives, is given in good faith. Eurostar Engineering Plastics makes no warranty or guarantee, express or implied about the information provided. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of Eurostar Engineering Plastics, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. Eurostar Engineering Plastics cannot be held responsible respectively liable for any loss incurred through the use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Eurostar Engineering Plastics or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

EUROSTAR Engineering Plastics, ZI - Rue de la Ferme Saint Ladre, BP2, F/95471 Fosses Cedex FRANCE,

Tel: + 33 1 34 47 47 00, Fax: + 33 1 34 47 47 18 - [www.eurostar-ep.com](http://www.eurostar-ep.com)

**DESCRIPTION** Starflam AFR470X2 is a Red Phosphorous Flame Retardant, Glass Fiber Reinforced Polyamide 66 Injection Molding Resin

PARAMETER	SETTING	UNIT
Drying Temperature	75 - 85	°C
Drying Time	4 - 6	hrs
Maximum Moisture Content	0.1	%
Mold Temperature	70-90	°C
Rear - Zone 1 Temperature	275 - 285	°C
Middle - Zone 2 Temperature	275 - 285	°C
Front - Zone 3 Temperature	275- 285	°C
Melt Temperature	275 - 285	°C

**PROCESSING PARAMETERS** : see above typical molding conditions.

**SAFETY** : Specific safety precautions must be taken when handling and processing this material. Please consult product MSDS or contact our technical service for details.

**PREDRYING** : This material is supplied in sealed bags. However further typical drying is required.

**BARRELS, SCREWS, MOULDS** : use wear resisting steel or alloy such as bimetallic cylinders, nitrided screws.

Source RJF, last update 01-07-2010

(1) Typical values for natural color unless specified otherwise. Do not constitute a specification. Significant variations are possible for colors

Starflam, Staramide and Starpylen are registered trademarks of EUROSTAR Engineering Plastics

All information, recommendation or advice giving by Eurostar Engineering Plastics Company, or any of its subsidiaries, affiliates or authorized representatives, is given in good faith. Eurostar Engineering Plastics makes no warranty or guarantee, express or implied about the information provided. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of Eurostar Engineering Plastics, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. Eurostar Engineering Plastics cannot be held responsible respectively liable for any loss incurred through the use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Eurostar Engineering Plastics or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

EUROSTAR Engineering Plastics, ZI - Rue de la Ferme Saint Ladre, BP2, F/95471 Fosses Cedex FRANCE,

Tel: + 33 1 34 47 47 00, Fax: + 33 1 34 47 47 18 - [www.eurostar-ep.com](http://www.eurostar-ep.com)