FORMPOLY GPP20THS (20%GLASS REINFORCED PP)

GENERAL

FPL offers a range of Polypropylene grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including FORMPOLY GPP20THS, which is heat stabilized, lubricated glass reinforced PP with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY GPP20THS

Medium Flow
Chemically coupled GF reinforced.
High Mechanical properties.
Excellent Heat Resistance
Easy processability
Good Heat Aging
Excellent dimensional stability.

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100'C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY GPP20THS is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Radiator Shroud Washing Machine Insulating Parts Automotive Interior Trim Roof Vents Automotive Parts

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	60
Elongation at Break	D638	%	5
Flexural Stress	D790	MPa.	80
Flexural Modulus	D790	MPa.	3000
Izod Impact Strength	D256	Kg Cm/ Cm	10
Notched Heat Deflection Temp - at 4.6 Kg / Cm ² load - at 18.5 Kg / Cm ² load	D648	'C	130 80
Specific Gravity Shrinkage	D792 D955	- %	1.06 0.3-0.7
Melt Flow Index	D1238	Grams/10min	5

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Pigmented colors would record lower mechanical properties as permitted by ASTM D 4066.

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com URL: www.formulatedpolymers.com HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600126 India



