FORMPOLY SPP530 (30% MINERAL REINFORCED PP)

GENERAL

FPL offers a range of Polypropylene grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including **FORMPOLY SPP530**, which is heat stabilized, Lubricated, Mineral reinforced PP with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLYSPP530

High Heat distortion and service temperature
Easy flow and solidification
Good mechanical and thermal properties.
UV stabilized
Easy processability
Good surface finish and Gloss
Excellent dimensional stability

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100'C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY SPP530 is supplied in 25 Kgs. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Speedometer parts Automotive head lamp Parts Automotive Interior Trim Handles Toys

Property	ASTM	Unit	Value
	Method		
Tensile Stress	D638	MPa.	28
Elongation at Break	D638	%	30
Flexural Stress	D790	MPa.	45
Flexural Modulus	D790	MPa.	3000
Izod Impact Strength	D256	Kg Cm/ Cm	5
Notched			
Heat Deflection Temp			
 at 4.6 Kg / Cm2 load 	D648	'C	130
- at 18.5 Kg / Cm2 load			5
Specific Gravity	D792	-	1.13
Shrinkage	D955	%	0.8-1.2
Melt Flow Index	D-1238	Grams/10 Min	8

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com URL: www.formulatedpolymers.com HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600126 India

