

FORMPOLY® GPP20FRV2 (20% GLASS REINFORCED PP- FR GRADE)

GENERAL

FPL offers a range of Polypropylene grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including **FORMPOLY® GPP20FRV2**, which is heat stabilized, lubricated glass reinforced PP with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY® GPP20FRV2

Flame retardant grade
High Mechanical properties.
Excellent Heat Resistance
Easy processability
Good Heat Aging
Excellent dimensional stability.

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY® GPP20FRV2 is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Radiator Shroud
Washing Machine Insulating Parts
Automotive Interior Trim
Roof Vents
Automotive Parts

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	50
Elongation at Break	D638	%	3.5
Flexural Stress	D790	MPa.	70
Flexural Modulus	D790	MPa.	2800
Izod Impact Strength Notched	D256	Kg cm/cm	3.5
Heat Deflection Temp - at 4.6 Kg/cm ² load - at 18.5 Kg/cm ² load	D648	°C	120 70
Specific Gravity	D792	-	1.10
Shrinkage	D955	%	0.3-0.7
Flammability	UL94	-	V2

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4101

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.



ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm