

FORMPOLY® PPMG30ST

(Glass Fibre and Talc Reinforced PP)

GENERAL

FPL offers a range of Polypropylene grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including **FORMPOLY® PPMG30ST**, which is heat stabilized, lubricated glass and talc reinforced PP with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY® PPMG30ST

Medium Flow

Moderate Mechanical properties.

Easy processability

Good dimensional stability.

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 80°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY® PPMG30ST is supplied in 25 Kg. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Radiator Shroud

Washing Machine Insulating Parts

Automotive Interior Trim

Roof Vents

Automotive Parts

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	45
Elongation at Break	D638	%	3
Flexural Stress	D790	MPa.	70
Flexural Modulus	D790	MPa.	3000
Izod Impact Strength Notched	D256	Kg cm/cm	8
Heat Deflection Temp - at 4.6 Kg/cm ² load - at 18.5 Kg/cm ² load	D648	°C	130 80
Specific Gravity	D792	-	1.10
Shrinkage	D955	%	0.2-0.5

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

