

FORMPOLY TPP20FR

(20% TALC REINFORCED PP-FR Grade)

GENERAL

FPL offers a range of Polypropylene grades from unfilled, glass fibre reinforced, mineral reinforced to flame retardant including **FORMPOLY TPP20FR**, which is heat stabilized, lubricated PP with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY TPP20FR

Meeting UL94 V0 requirements
Easy flow and fast solidification
Good mechanical and thermal properties.
Anti dripping
Easy processability
Excellent dimensional stability

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 100°C for 2 to 3 hours for good surface finish.

PACKING

FORMPOLY TPP20FR is supplied in 25 Kgs. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Switch parts
Automotive fire alarm indicator
Roofing parts

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	30
Elongation at Break	D638	%	6
Flexural Stress	D790	MPa.	40
Flexural Modulus	D790	MPa.	2500
Izod Impact Strength Notched	D256	Kg cm/cm	4
Heat Deflection Temp - at 4.6 Kg/cm ² load - at 18.5 Kg/cm ² load	D648	°C	125 80
Specific Gravity	D792	-	1.24
Shrinkage	D955	%	0.5- 0.8
Melt Flow Index	D1238	g/10min	12

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.



A ISO/TS 16949. ISO 9001 & ISO 14001 & ISO 18000 certified