FORMPOLY® TPP40 NCO

(40% Talc Reinforced PP - Opaque Grade)

GENERAL

FPL offers range Polypropylene grades from unfilled. glass fibre reinforced. reinforced flame mineral to retardant including FORMPOLY® TPP40 NCO. which heat **lubricated** Talc stabilized. reinforced PP with excellent mechanical / thermal properties and reduced shrinkage.

FORMPOLY® TPP40 NCO

Easy flow and fast solidification Good mechanical and thermal properties. UV stabilized Easy processability Good surface finish and Gloss

PRE-DRYING

of FPL grades can normally be taken for direct processing. However, in ed, case the material is exposed to atmosphere, it is advisable to predry dry the material at 80°C for 2 to 3 at hours for good surface finish.

PACKING

FORMPOLY® TPP40 NCO is supplied in 25 Kgs. dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

Speedometer parts
Automotive Head Lamp Parts
Control housing
Handles
Timing Belts
Automotive inner parts

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	28
Elongation at Break	D638	%	4
Flexural Stress	D790	MPa.	50
Flexural Modulus	D790	MPa.	3800
Izod Impact Strength	D256	kg cm/cm	4
Notched			
Heat Deflection Temp			
- at 4.6 Kg/cm² load	D648	°C	140
- at 18.5 Kg/cm² load		°C	90
Specific Gravity	D792	_	1.25
Shrinkage	D955	%	0.2-0.5
Melt Flow Index	D1238	g/10min	12

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen Coloured grades would record slightly lower mechanical properties as permitted by ASTM D-4066

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: info@formulatedpolymers.com

URL: www.formulatedpolymers.com

HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600 124 India.

ISO 9001:2015, IATF 16949: 2009 & ISO 14001: 2015 Certified Firm

