

FORMPOLY PPOGF30 (30%GF Reinforced PPO)

GENERAL

FPL offers a range of Engineering Plastic grades from unfilled, glass fibre reinforced, mineral reinforced, impact modified to flame retardant for most demanding conditions and extreme requirements including **PPOGF30** which is Glass fibre reinforced PPO with high stiffness.

FORMPOLY PPOGF30

- High heat resistance
- Low warpage
- Good Surface finish
- Easy flow and fast solidification
- Easy processability

PRE-DRYING

FPL grades can normally be taken for direct processing. However, in case the material is exposed to atmosphere, it is advisable to pre-dry the material at 80°C for 1 to 2 hours for good surface finish.

PACKING

FORMPOLY PPOGF30 is supplied in 25 Kg. Dry, ready to mould, in sealed bags to prevent the uptake of moisture.

APPLICATION

- Electrical meter parts
- Automotive ignition
- Motor housing
- Ampere meter parts
- Flow regulators

Property	ASTM Method	Unit	Value
Tensile Stress	D638	MPa.	100
Elongation at Break	D638	%	3
Flexural Stress	D790	MPa.	160
Flexural Modulus	D790	MPa.	9000
Izod Impact Strength Notched	D256	Kg Cm/ Cm	9
Heat Deflection Temp - at 18.5 Kg / Cm ² load	D646	°C	145
Specific Gravity	D792	-	1.27
Shrinkage	D955	%	0.1-0.3
Water absorption at Equilibrium	D 570	%	0.12
Vicat VST/B/120	D 1525	C	150

Conditioned test specimen. All results are measured under Dry-as-moulded natural test specimen
Pigmented colors would record lower mechanical properties as permitted by ASTM D 4066.

The information present here is for general guidance. It is given in good faith but no warrant is attached

FORMULATED POLYMERS LIMITED

Manufacturers of Engineering Plastics Compounds

Ph: +91-44-26811236,7:: Fax:2681 1275 E Mail: formpoly@vsnl.com URL: www.formulatedpolymers.com
HO & Works: 59, SIDCO Industrial Estate, Thirumazhisai, Chennai - 600124India



A ISO/TS 16949, ISO 9001 & ISO 14001 certified Firm